

Technical Data Sheet

BAYFERROX® 120

Description

| | |
|------------------------|---|
| Type | Red pigment |
| Delivery form | Powder |
| Chemical class | Synthetic iron oxide α - Fe_2O_3 |
| Colour Index | Pigment red 101 (77491) |
| CAS-No. | 1309-37-1 |
| REACH registration no. | 01-2119457614-35 |

Specified Color Data

| Colour values and tinting strength | | | | | |
|---|---------------|-----|---|-----|-----------------------|
| Standard | Bayferrox 120 | | | | |
| Year | 2021 | | | | |
| Binder: | Full shade | | Reduction ⁴⁵ with titanium dioxide (1:5) | | Test method |
| Test paste based on a non drying alkyd resin | min | max | min | max | No. 001 ⁴¹ |
| ΔL^* | -0.5 | 0.5 | | | |
| Δa^* | -1.0 | 1.0 | -1.0 | 1.0 | |
| Δb^* | -1.2 | 1.2 | -1.3 | 1.3 | |
| ΔE^*_{ab} | | 1.5 | | 1.5 | |
| Binder: Barytes | | | 95 | 105 | Test method |
| Relative tinting strength [%] | | | | | No. 003 ⁴¹ |

Specified Technical Data

| Technical Data | min | max | Test method |
|------------------------------------|-----|------|-------------------------------------|
| Water-soluble content [%] | | 0.5 | similar to DIN EN ISO 787-3:2000 |
| Sieve residue (0.045 mm sieve) [%] | | 0.06 | DIN EN ISO 787-7:2009 |
| pH value | 4 | 8 | DIN EN ISO 787-9:1995 |

BAYFERROX® 120

Informative Technical Data (guide values)

| | | | Test method |
|---|---|-----------|---|
| α - Fe ₂ O ₃ content [%] ⁵³ | > | 99.1 | Information about the determination of iron oxide ⁴¹ |
| Loss on ignition at 1000 °C, 0.5 h [%] | < | 0.6 | DIN 55913-2:1972 |
| Moisture content (after production) [%] | < | 0.5 | DIN EN ISO 787-2:1995 |
| Particle shape | | spherical | Electron micrographs |
| Predominant particle size [µm] | ~ | 0.12 | Electron micrographs |
| Oil absorption [g/100 g] | ~ | 28 | DIN EN ISO 787-5:1995 |
| Tamped density [g/ml] | | 0.7 - 1.1 | similar to |
| | | | DIN EN ISO 787-11:1995 |
| Density [g/ml] | ~ | 5.0 | DIN EN ISO 787-10:1995 |

⁴¹ Obtainable from LANXESS Deutschland GmbH, Business Unit Inorganic Pigments, [mailto: ipg.product-information@lanxess.com](mailto:ipg.product-information@lanxess.com)

⁴⁵ Colour values after matching of the tinting strength parameter Y, i.e. $\Delta L^*=0$

⁵³ Minor elements may arise from the raw materials used. However, these are firmly bound to the crystal lattice as ions.

BAYFERROX® 120

Packaging

Grades are delivered in different packaging materials. Please ask your local contact about the packaging for the grade in question or send an enquiry mailto: ipg.product-information@lanxess.com

Transport and Storage

| | |
|--|--|
| General storage conditions: | Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. |
| Special conditions for opened packaging: | Close bags after use to prevent the absorption of moisture and contamination. |
| Shelf life: | <p>This product has an excellent shelf life. We recommend that this product is used within ten years of the date of manufacture and limit our product warranty to this period. During the first ten years after the date of manufacture we are able to ensure compliance with this specification, provided the material has been stored as stated above and the packaging materials remain undamaged. It must be taken into account that the packaging mean can have a shelf life considerably shorter than the one for this product. All recommendations and warnings given on the packaging must strictly be adhered to. Deviations from storage conditions can lead to undesired changes on side of the packaging materials. These succumb to ageing which may also lead to compromising their capability. Concerning their estimated service life we differentiate between the following packaging materials:</p> <p>All kinds of bags (Paper and PE) 5 years All kinds of Bulk bag 3 years</p> <p>With respect to our Bulk Bags we recommend to avoid UV-radiation because the sewing material of the lifting loops is stabilized against degradation by UV-radiation for appr. 1000 h incident sun radiation for the climate of Central Europe. A more intense sun radiation can shorten this period significantly. In cases of doubt the lifting loops must be checked thoroughly.</p> |

Safety

| | |
|------------------------|--|
| Classification | <p>The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations.</p> <p>In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured.</p> |
| Additional Information | <p>The safety data sheet should be observed. This contains information on handling, product safety and ecology.</p> <p>The safety data sheet is available at www.bayferrox.com.</p> |

BAYFERROX® 120

Information concerning food contact regulations

This product complies with the regulatory requirements listed hereafter or may be used in accordance with those.

Remark:

We can only refer to regulations dealing directly with pigments or colourants. The compliance with laws and regulations dealing with the finished article lies completely in the responsibility of the manufacturer of those articles.

| | |
|-------------------|--|
| Council of Europe | Resolution AP(89)1 on the use of colourants in plastic materials coming into contact with food |
| France | Circulaire n°176 consolidée du 2 décembre 1959 modifiée relative aux pigments et colorants des matières plastiques et emballages. |
| Germany | BfR IX Empfehlung IX des Bundesinstituts für Risikobewertung vom 1. Juni 2019 |
| Italy | Decreto Ministeriale del 21/03/1973 Disciplina igienica degli imballaggi, recipienti, utensili, destinati a venire in contatto con le sostanze alimentari o con sostanze d'uso personale. |
| Netherlands | Warenwetregeling verpakkingen en gebruiksartikelen: Regeling van de Minister van Volksgezondheid, Welzijn van 14 maart 2014, kenmerk 328583-117560-VGP, houdende vaststelling van de Warenwetregeling verpakkingen en gebruiksartikelen die in contact komen met levensmiddelen. |
| Spain | Real Decreto 847/2011, de 17 de junio, por el que se establece la lista positiva de sustancias permitidas para la fabricación de materiales poliméricos destinados a entrar en contacto con los alimentos. |
| Switzerland | 817.023.21 Verordnung des EDI über Materialien und Gegenstände, die dazu bestimmt sind, mit Lebensmitteln in Berührung zu kommen (Bedarfsgegenständeverordnung) vom 16. Dezember 2016 (Stand am 1. Dezember 2019) |
| Australia | AS 2070-1999 Plastic materials for food contact use |
| Brazil | RDC Nº 52 Dispõe sobre corantes em embalagens e equipamentos plásticos destinados a estar em contato com alimentos. |
| China | Red iron oxides are listed in GB 9685-2016 with FCA number 0410. For detailed information about limitations please refer to the standard itself. |
| Japan | JHOSPA This product complies with Japanese Food sanitation law amended in June 2020. As there is no specific positive list for pigments the JHOSPA list for pigments remains valid until further announcement. |
| MERCOSUR | GMC/RES. Nº 15/10 REGLAMENTO TÉCNICO MERCOSUR SOBRE COLORANTES EN ENVASES Y EQUIPAMIENTOS PLÁSTICOS DESTINADOS A ESTAR EN CONTACTO CON ALIMENTOS |
| USA | FDA 21 CFR § 178.3297 (Colorants for polymers) |

BAYFERROX® 120

Status of Registration

| The components of this product are listed on the following inventories: | | | | |
|---|-----------------------|----------------|--------------------|-----------------------|
| Europe: EINECS | USA: TSCA | Canada: DSL | Australia: AICS | New Zealand: NZIOC |
| Philippines: PICCS | Japan: ENCS + ISHL | Korea: ECL | China: IECSC | Taiwan: NECSI |